

Asbestos Free

Technical Data Sheet

MATERIAL PROPERTIES*:

Colour:

Blue-Gard® 3300

Black

Composition:

Aramid fibres with a neoprene binder

Fluid Services:

Water, saturated steam³, refrigerants, oils and fuels

Temperature¹, °F (°C)

Minimum:

-100 (-73)

Continuous Maximum:

+400 (+205)

Maximum:

+700 (+371)

Pressure¹, Maximum, psig (bar):

1200 (83)

P x T (max.)¹, psig x °F (bar x °C):

1/32 and 1/16":

350,000 (12,000)

1/8"

250,000 (8,600)



TYPICAL PHYSICAL PROPERTIES*:

ASTM F36	Compressibility, average, %:	10
ASTM F36	Recovery, %:	55
ASTM F38	Creep Relaxation, %:	20
ASTM D1708	Tensile, Across Grain, psi (N/mm ²):	1800 (12.4)
ASTM F1315	Density lbs/ft ³ (grams/cm ³):	110 (1.76)
ASTM F433	Thermal Conductivity (K), W/m·K (Btu in/ hr ft ² °F):	0.29 - 0.38 (2.00 - 2.65)

SEALING CHARACTERISTICS*

	ASTM F37B Fuel A	ASTM F37B Nitrogen	DIN 3535 Nitrogen
Gasket Load, psi (N/mm2):	500 (3.5)	3000 (20.7)	4640 (32)
Internal Pressure, psig (bar):	9.8 (0.7)	30 (2)	580 (40)
Leakage	0.2 ml/hr.	0.5 ml/hr	0.05 cc/min

Notes: * This is a general guide and should not be the sole means of selecting or rejecting this material. This data sheet covers basic information, for more comprehensive information, please contact us. ASTM test results in accordance with ASTM F-104; properties 1 Based on ANSI RF flanges at our preferred torque. When approaching maximum pressure, continuous operating temperature, minimum temperature or 50% of maximum P x T, consult us. Minimum temperature rating is conservative. 2 Indicates electric current arced around and not through the gasket. Dielectric strength is higher than indicated. 3 These styles are not preferred choices for steam service, but are successful when adequately compressed. Minimum recommended assembly stress = 4,800psi. Preferred assembly stress = 6,000-10,000psi. Gasket thickness of 1/16" strongly preferred. Re-torque the bolts/studs prior to pressurizing the assembly. For saturated steam above 150psi or superheated steam, consult us.



Certificate Number: 14352
 ISO 9001



Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

Web: www.epdm.co.uk

E-Mail: Sales@epdm.co.uk

Contact

Telephone: +44 (0)1625 573971
 FAX: +44 (0)1625 573250
 Munsch & Co/PTM Ltd
 Units AG2/3 Clarence Mill
 Clarence Road, Bollington
 Macclesfield, Cheshire
 SK10 5JZ
 United Kingdom