

Technical Data Sheet

Nitrile Rubber BS2751 BA70

CHEMICAL DESCRIPTION: Acrylonitrile Butadiene, Nitrile Butadiene Rubber (NBR)

PHYSICAL PROPERTIES

TENSILE STRENGTH:	13 MPa (Min)
ELONGATION AT BREAK:	350%
HARDNESS RANGE:	70° Sh. A +/- 5°
HEAT RESISTANCE:	-30° - + 110°C
SPECIFIC GRAVITY:	1.28 +/-0.02
COMPRESSION SET:	30%
22 Hours @ 70°C	



CHEMICAL RESISTANCE

WATER:	Good to Excellent	
DILUTE ACIDS & BASES:	Good	
ALKALIS:	Good to Excellent	
OZONE:	Poor	
HYDROCARBONS:	Moderate	
SOLVENTS:	Moderate	
VOLUME SWELLING:	ASTM 5 Inc. Vol Oil %	IRM903 Inc. Vol. Oil %
70 HOURS @ 70°C	5	20

This is a British Standard Nitrile Rubber to BS2751. Using a recognised standard ensures that the material will always comply to it no matter who the manufacturer is.

This ensures continuity of operation which can vary if non-standard materials are used.

ELASTOMERS

Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

www.epdm.co.uk

E-Mail: Sales@epdm.co.uk

Contact

Telephone: +44 (0)1625 573971
 FAX: +44 (0)1625 573250
 Munsch & Co/PTM Ltd
 Units AG2/3 Clarence Mill
 Clarence Road, Bollington
 Macclesfield, Cheshire
 SK10 5JZ
 United Kingdom



Certificate Number: 14352
 ISO 9001

